



# FOAMULAR® Extruded Polystyrene (XPS) Fabrication Billets

## Product Data Sheet

### Description

FOAMULAR® Extruded Polystyrene (XPS) Fabrication Billets are manufactured from rigid sheets of foam made using Owens Corning's patented Hydrovac® process technology. The unique closed-cell structure of FOAMULAR® XPS insulation makes it highly resistant to moisture, low in water absorption but high in insulating capability.

FOAMULAR® XPS Fabrication Billets are factory laminated using a specially formulated polyurethane-based adhesive under strict process controls to ensure performance.

The primary function of the FOAMULAR® XPS Fabrication Billet product is to provide raw stock to commercial pipe fabricators from which individual pipe insulation parts can be cut.

### Key Features

- Compressive strength of 25 psi
- Exceptional thermal efficiency
- Long service life
- Reduced overall installation costs
- Manufactured in the U.S.A.
- Available in several standard sizes:
  - 8" x 48" x 73" MTO
  - 20" x 48" x 73" MTO
  - 24" x 48" x 73" Stock

### Typical Physical Properties

Property	Test Method <sup>1</sup>	Value
Density, lb./ft <sup>3</sup> (kg/m <sup>3</sup> )	ASTMD1622	1.55 (25)
Thermal Conductivity <sup>2,3</sup> , maximum, Btu•in/ft <sup>2</sup> •hr•°F 180 days @ 75°F mean temperature	ASTM C518	0.200 (0.029)
Compressive Strength <sup>2,4</sup> , minimum, psi (kPa)	ASTM D1621	25 (173)
Water Absorption <sup>2,5</sup> , maximum, % by volume	ASTM C272	0.15
Water Vapor Permeance <sup>2,6</sup> maximum, perm (ng/Pa•s•m <sup>2</sup> )	ASTM E96	1.5 (86)
Dimensional Stability <sup>2</sup> , % linear change	ASTM D2126	1.0
Flame Spread <sup>2,7,8</sup>	ASTM E84	5
Smoke Developed <sup>2,7,8</sup>	ASTM E84	175
Service Temperature, maximum, °F (°C)		-100 to 165 (-73 to 74)
Linear Coefficient of Thermal Expansion, in/in•°F	ASTM E228	3.5 x 10 <sup>-5</sup> (6.3 x 10 <sup>-5</sup> )

1. Sample modified as required to meet applicable test method.

2. XPS foam core value

3. k means the apparent thermal conductivity. The lower the value, the greater the insulation power.

4. Values at yield or 10% deflection, whichever occurs first.

5. Data ranges from 0.00 to value shown due to the level of precision of the test method.

6. Water vapor permeance decreases as thickness increases.

7. These laboratory tests are not intended to describe the hazard presented by this material under actual fire conditions.

8. Fire performance of FOAMULAR® 4" thick product only. Thicker products may have different fire performance characteristics. Due to limits on the equipment used to test per ASTM E84, Owens Corning™ FOAMULAR® XPS Fabrication Billets have not been tested.

### Product Applications

FOAMULAR® XPS  
Fabrication Billets:

- Industrial (Non-plenum) Applications
- High Humidity and High Moisture Conditions
- Low Temperature Systems
- Typical Industrial Uses
  - Ammonia/liquid refrigeration lines
  - Chilled water piping
  - Cold storage systems
  - Freezer rooms
  - Pharmaceutical plants
  - Refrigeration equipment
  - Transport pipelines
  - Direct burial applications

### Technical Information

Owens Corning has developed an Installation Guide for Low Temperature Pipe Insulation to assist engineers, architects, and contractors with the proper installation of pipe insulation made from FOAMULAR® XPS Fabrication Billets. This guide is available at [www.owenscorning.com](http://www.owenscorning.com).

FOAMULAR® XPS Fabrication Billets are available to Owens Corning Certified Fabricators. To learn more about becoming an Owens Corning Certified Fabricator, contact your local area sales manager. For more information, call 1-800-GET-PINK®.

Technical questions can be submitted to:  
[GETTECH@owenscorning.com](mailto:GETTECH@owenscorning.com).



# FOAMULAR® Extruded Polystyrene (XPS) Fabrication Billets

## Product Data Sheet

### Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at [www.sustainability.owenscorning.com](http://www.sustainability.owenscorning.com).

### Warranty

FOAMULAR® XPS Fabrication Billets are made from FOAMULAR® XPS insulation. FOAMULAR® XPS insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all ASTM C578 properties. See actual warranty for complete details, limitations and requirements at [www.foamular.com](http://www.foamular.com) or [www.owenscorningcommercial.com](http://www.owenscorningcommercial.com).

### Notes

- Fire performance of products fabricated using FOAMULAR® XPS Pipe Fabrication Billets may vary in the field depending on facings and adhesives used in the fabrication process. Fabricators should be consulted if composite fire performance is required.
- FOAMULAR® XPS Fabrication Billets and the subsequent parts and pipe sleeves that are fabricated from it are subject to deterioration from prolonged exposure to ultraviolet light and sun exposure. Procedures should be established during fabrication, shipment, storage, and eventual product use that limit total direct exposure to ultraviolet light to a maximum of 30 days over the life of the material.

### Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.

Scientific Certification Systems (SCS) provides independent verification of recycled content building materials and verifies recycled content claims by a manufacturers.



**OWENS CORNING FOAM INSULATION, LLC**  
ONE OWENS CORNING PARKWAY  
TOLEDO, OHIO 43659  
**1-800-GET-PINK®**  
[www.owenscorning.com](http://www.owenscorning.com)

Pub. No. 10013996-C. Printed in U.S.A. November 2012. THE PINK PANTHER™ & ©1964-2012 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. ©2012 Owens Corning.

